IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant:

Dong-ho Chang

Examiner:

Not Assigned

Appl. No:

Not Assigned

Art Unit:

Not Assigned

Filing Date:

November 5, 2001

Date:

November 5, 2001

For:

TARPAULIN USING RESIN COMPOSITION FOR PRESS-COATING AND

METHOD FOR PREPARING THE SAME

Honorable Commissioner of Patents Washington, D.C. 20231

PRELIMINARY AMENDMENT

This paper is being filed concurrently with the associated application. Three additional dependent claims have been added. The application now contains two independent claims and a total of ten claims, which are all covered by the original filing fee. As such, no additional fees are believed to be due. If any additional fees are required, please consider this a petition for payment of them and charge them to Deposit Account 15-0450.

Please amend the above-identified application as follows:

In The Claims:

Please amend the following claims:

Claim 3, line 1, delete "or claim 2".

Claim 4, line 1, delete "or claim 2".

Claim 5, line 1, delete "or claim 2".

Please add the following new claims:

- 8. (New) The tarpaulin according to claim 2, wherein said ethylene-propylene copolymer satisfies the following condition:
 - 1) ethylene content : $20 \sim 30$ mole%;
 - 2) melt index : $15 \sim 30 \text{ g/}10 \text{ minutes}$
 - 3) density: $0.890 \sim 0.900 \text{ g/cm}^3$.
- 9. (New) The tarpaulin according to claim 2, wherein said ethylene-octene random copolymer satisfies the following condition:
 - 1) ethylene content : $60 \sim 90$ parts by weight;
 - 2) octene content : $40 \sim 10$ parts by weight
 - 3) pattern viscosity: $1.5 \sim 10$ at ML 1+4 (121°C)
- 10. (New) The tarpaulin according to claim 2, wherein said styrene-ethylene-butene block copolymer satisfies the following condition:
 - 1) pattern viscosity: $1.0 \sim 18$ at ML 1+4 (121°C)

REMARKS

The above claims have been amended and new claims added to more closely correspond them to United States claiming practice, namely, by removing multiple dependencies. These amendments to the claims are fully supported by the literal translation into English of the specification as filed in Korea, and do not introduce new subject matter. The claims as amended are provided on clean sheets.

Respectfully submitted,

R. Eric Gaum

Registration Number 39,199 regaum@hahnlaw.com

R. Ein Ham

REG/cam

Hahn Loeser & Parks LLP (formerly Oldham & Oldham Co., L.P.A.) Twin Oaks Estate 1225 West Market Street Akron, Ohio 44313-7188 330.864.5550 (voice) 330.864.7986 (fax)

Attorney Docket: 6978-7

CLAIMS AMENDED OR ADDED

- 3. (Amended) The tarpaulin according to claim 1, wherein said ethylene-propylene copolymer satisfies the following condition:
 - 1) ethylene content: 20 ~ 30 mole%;
 - 2) melt index : $15 \sim 30$ g/10 minutes
 - 3) density: $0.890 \sim 0.900 \text{ g/cm}^3$.
- 4. (Amended) The tarpaulin according to claim 1, wherein said ethylene-octene random copolymer satisfies the following condition:
 - 1) ethylene content : $60 \sim 90$ parts by weight;
 - 2) octene content : $40 \sim 10$ parts by weight
 - 3) pattern viscosity : $1.5 \sim 10$ at ML 1+4 (121°C)
- 5. (Amended) The tarpaulin according to claim 1, wherein said styrene-ethylenebutene block copolymer satisfies the following condition:
 - 1) pattern viscosity: $1.0 \sim 18$ at ML 1+4 (121°C)
- 8. (New) The tarpaulin according to claim 2, wherein said ethylene-propylene copolymer satisfies the following condition:
 - 1) ethylene content : $20 \sim 30$ mole%;
 - 2) melt index : $15 \sim 30 \text{ g/}10 \text{ minutes}$
 - 3) density: $0.890 \sim 0.900 \text{ g/cm}^3$.

- 9. (New) The tarpaulin according to claim 2, wherein said ethylene-octene random copolymer satisfies the following condition:
 - 1) ethylene content: $60 \sim 90$ parts by weight;
 - 2) octene content: $40 \sim 10$ parts by weight
 - 3) pattern viscosity: $1.5 \sim 10$ at ML 1+4 (121°C)
- 10. (New) The tarpaulin according to claim 2, wherein said styrene-ethylene-butene block copolymer satisfies the following condition:
 - 1) pattern viscosity: $1.0 \sim 18$ at ML 1+4 (121°C)